

GUTEX® Klebe- und Spachtelputz Data Sheet

Fibre-reinforced, cementitious dry mortar (inorganic mortar)

(A system component in GUTEX Thermowall based composite thermal insulation systems)

Product Features and Advantages
<ul style="list-style-type: none"> – Good bonding to all properly prepared, intact and suitable substrates – High water vapour permeability – Superior bonding – Easy to apply, excellent workability – Superb plasticity – Suitable for spray application with all common mix and continuous feed systems
Description and Materials
GUTEX Klebe- und Spachtelputz is a hydraulic setting mortar in the Mörtelgruppe (mortar class) P II as per DIN 18550
Binder:
White cement and calcium hydroxide, dispersion powder
Additives:
Quartz, mineral extenders
Admixtures:
Additives to improve water retentivity and bonding
Batch water:
Pure water without additives
Applications
GUTEX Klebe- und Spachtelputz mortar is suitable for:
<ul style="list-style-type: none"> – Adhesion of GUTEX Thermowall/-gf – Base coat for GUTEX Thermowall stucco systems – Reinforcement with GUTEX Universal-Armierungsgewebe (universal reinforcement mesh)
Intended areas of use:
Interior and exterior
Instructions
Substrate:
Substrate temperature must be above freezing and the substrate surface must be intact, oil-free, dirt- and dust-free and free of any residues that could prevent effective bonding. The bonding of the base coat must be flawless. Moreover, the substrate surface must be uniformly dry at the time of application.
Substrate preparation:
<ul style="list-style-type: none"> – Prime sandy, dusty substrates. – Uniformly dampen absorbent substrates with water before applying. – If required, apply an isolating primer (GUTEX Isoliergrund) to new and old stucco coats.

Preparation for use:
Mix 25 kg of GUTEX Klebe- und Spachtelputz mortar with approx. 6,3 l of clean water, making sure there are no lumps. Wait 5 minutes and stir again, adding water to adjust the mixture to specific conditions and workability requirements. Do not allow hardened or dried material to be remixed into the mixture.
Application:
Apply GUTEX Klebe- und Spachtelputz mortar with a stainless steel towel, serrated trowel or final coat spray system. Water mixture must be adjusted for specific machine/pump. Tools and equipment, technique and substrate all have a significant effect on the quality of the final result.
Equipment cleaning:
Clean and rinse with water after use.
Application temperature:
Lowest substrate and ambient temperature is 5°C. Do not apply, if frost is expected overnight or the substrate temperature is below freezing.
Pot life:
At 20°C, approx. 60 minutes
Hardening:
The hardening lasts 1 day/mm depending on weather conditions. Higher relative humidity or lower temperatures will slow down the hardening process. Protect GUTEX Klebe- und Spachtelputz from quick drying, exposure to intense sunshine or wind. (Threat of cracking, absorptive surface, insufficient hardening and bonding)
Drying:
Hardens to a large extent hydraulically
Coverage:
<ul style="list-style-type: none"> – Used as an adhesive: 4 - 5 kg/m² – Used as base coat: 3 - 4 kg/m² – Used with reinforcement meshing: 3 - 4 kg/m²
Additional Information
Packaging unit:
25 kg bag
Storage:
Store dry. Exposure to moisture may cause lumps to form. The maximum storage time appears in the batch code on the plasterbag: digit 1 = final digit of the year, digit 2+3 = calendar week
Example: 3450013223 - shelf life expires at the end of the 45th week in 2013

Transport:

No special precautions or instructions necessary. Does not require labeling.

Safety precautions:

Wet mortar and plaster are alkaline and may cause alkali burns, therefore suitable clothing and eye protection must be worn when handling these materials. In the event of contact, rinse thoroughly with water. See a doctor immediately if this product has had contact to the eyes.

Disposal:

If the material is hardened, it may be disposed of, subject to local applicable laws, with regular household waste.

All rights reserved. Henselmann GmbH + Co KG shall not be held liable for any damage resulting from error or misprinting. The technical data provided herein is subject to change. Although all of the information herein was up to date at the time of its publication, the publication of superseding information renders the old information invalid. The suitability of this product for applications not specified in this data sheet is not guaranteed. Warranty and liability claims are subject to the terms of Gutex's General Terms of Business.

